



## UNDERLAY MAT BIOlay 1.5

Pressure-stable, heat and sound insulation underlay made from organic latex and mineral fillers.

- ◇ Format 1 x 10 m
- ◇ Strength 1,5 mm
- ◇ Enhanced walking comfort
- ◇ Sound and noise absorption (20 dB)
- ◇ Pressure-resistant (1677 kPa/m<sup>2</sup>) and highly elastic
- ◇ With integrated vapor barrier film
- ◇ Made of BIO latex and mineral fillers
- ◇ Renewable resource
- ◇ Recyclable raw material

Technical Specifications	Standard	LVT/SPC 1.5
Strength	EN 1849 - 1	1,5 mm
Specific weight	EN 1849 - 1	950 kg / m <sup>3</sup>
Impact sound	UNE 104-B 717/12	20 dB
Walking sound	UNE 104-B 717/12	38%
Fire behavior	DIN 4102	B <sub>r</sub> S1
Thermal conductivity	EN 12667	0,00912 m <sup>2</sup> K/w
Compressive strength	DIN EN 826	≥ 666 kPa
Protection against moisture	DIN EN 12086	≥ 52 m
Suitable for underfloor heating		Yes
Chair roll alignment		Yes

### Processing notes

The underlay mat should be laid with white textile side up and the vapor barrier film down to the ground.



Article No.	Facido No.	Description	EAN	Pack/Pallet
143642	106102208	Underlay mat BIOlay 1.5, 1 x 10 m	7640370940372	40